

POLYTEC 500 HMW AT

POLYTEC 500 UHMW AT (antistatic) is a high density polyethylen with high molecular weight and added an antistatic load, that presents electrostatic dissipative properties that do not modify the molecular structure or fundamental properties of the base product (POLYTEC 500 HMW).

This product is especially indicated in components of packaging machinery that operate with high speed lines.

PROPERTIES	UNITS	TEST METHODS	VALUES
Properties			
Density	g/cm ³	ISO 1183-1	0.96
Water absorption at saturation in water of 23°C	%	-	0.01
Mechanical Properties at 23°C			
Tensile stress at yield	MPa	ISO 527-1/-2	28
Tensile strain at yield	%	ISO 527-1/-2	10
Nominal tensile strain at break	%	ISO 527-1/-2	>50
Tensile modulus of elasticity	MPa	ISO 527-1/-2	1300
Compressive stress at 1/2/5 % nominal strain	MPa	ISO 604	12/18.5/26.5
Flexural strength	MPa	ISO 178	27
Charpy impact strength-unnotched	KJ/m ²	ISO 179-1/1eU	No break
Charpy impact strength- notched	KJ/m ²	ISO 179-1/1eA	105P
Charpy impact strength- notched (double 14° notch)	KJ/m ²	ISO 11542-2	25
Ball indentation hardness	N/mm ²	ISO 2039-1	48
Shore hardness D (15s)	-	ISO 2039-2	62
Relative weight loss during a wear test in "sand/water- slurry"	-	ISO 15527	350
Thermal Properties			
Melting temperature (DSC, 10°C/min)	°C	ISO 11357-1/-3	135
Thermal conductivity at 23°C	W/(K.m)	-	0.40
Average coefficient of linear thermal expansion between 23 and 100 °C	m/(m.K)	-	150x10 ⁻⁶
Temperature of deflection under load: method A:1.8 MPa	°C	ISO 75-1/-2	44
Vicat softening temperature- VST/B50	°C	ISO 306	80

POLYTEC 500 HMW AT

Max. allowable service temperature in air for short periods	°C	-	120
Max. allowable service temperature in air continuously for 20h	°C	-	80
Min. Service temperature	°C	-	-100
Oxygen Index for flammability	%	ISO 4589-1/-2	<20
Electrical Properties			
Surface resistance	Ohm	-	>10 ¹¹

Note: 1g/cm³ = 1,000 kg/m³; 1Mpa= 1N/mm² ; 1kV/mm = 1MV/m

* These data are very useful for the choice of material. The data listed here are indicative values and should not be used to establish specification limits of the material. From these values may not be deducted a legally binding of security of certain properties or the suitability for a particular application.